

Specifications

Art Board /Gloss

Physical Test	Unit	Tolerance	200g/m ²	216g/m ²	250g/m ²	270g/m ²	300g/m ²	350g/m ²	Test Method
Thickness	μm	±4%	173	201	228	253	300	350	ISO 534
Roughness(PPS)	μm	±0.3	1.3	1.5	1.6	1.6	1.8	2.3	ISO 8791
Brightness	%ISO	±1.5	89	89	89	89	89	89	ISO 2470
Opacity	%	±2	98	98	98	98	98	98	ISO 2471
Gloss	%	±5	70	70	70	70	70	70	T 480

Art Board /Matte

Physical Test	Unit	Tolerance	200g/m ²	216g/m ²	250g/m ²	270g/m ²	300g/m ²	350g/m ²	Test Method
Thickness	μm	±4%	198	216	248	276	313	365	ISO 534
Roughness(PPS)	μm	±0.3	1.7	1.7	1.8	1.8	2.0	2.3	ISO 8791
Brightness	%ISO	±1.5	89	89	89	89	89	89	ISO 2470
Opacity	%	±2	98	98	98	98	98	98	ISO 2471
Gloss	%	±5	30	30	30	30	30	30	T 480

Gold Huasheng(Suzhou Industrial Park) Co., Ltd.

Add: No.2 Jinsheng Road, Shengpu, Suzhou Industrial Park, Jiangsu, China

Tel:+86-512-62832623

Free Hot Line: +86-8008282009

Website: www.goldhs.com.cn