



TECHNICAL DATA

Product Description

Brightest white paper and boards made with FSC pulps from certified and controlled sources.

Technical Data

	Method		+ / -	80 g / m ²	90 g / m ²	100 g / m ²	120 g / m ²	140 g / m ²	160 g / m ²	200 g / m ²
Basis weight	ISO 536	g / m ²	5 %	80	90	100	120	140	160	200
Caliper	ISO 534	µm	5 %	92	103	114	134	155	176	216
Bulk				1,15	1,14	1,14	1,12	1,11	1,10	1,08
Whiteness (CIE)	ISO 11475	%	3	168	168	168	168	168	168	168
Roughness (Bendtsen)	ISO 8791	m l / m in	30	80	80	80	80	80	80	80
Opacity	ISO 2471	%	>	90	92	92	94	95		
Moisture content	ISO 287	%	1,0	5,5	5,5	5,5	5,5	6,5	6,5	6,5

	Method		+ / -	250 g / m ²	300 g / m ²	320 g / m ²	350 g / m ²	400 g / m ²	500 g / m ²	700 g / m ²
Basis weight	ISO 536	g / m ²	5 %	250	300	320	350	400	500	700
Caliper	ISO 534	µm	5 %	268	318	339	368	420	535	749
Bulk				1,07	1,06	1,06	1,05	1,05	1,07	1,07
Whiteness (CIE)	ISO 11475	%	3	168	168	168	168	168	168	168
Roughness (Bendtsen)	ISO 8791 -2	m l / m in	30	80	80	80	80	80	80	80
Opacity	ISO 2471	%	>							
Moisture content	ISO 287	%	1,0	6,5	6,5	6,5	6,5	6,5	7,0	7,0



The mark of responsible forestry